

# OM2 (50/125 $\mu$ m) Bending Insensitive Multimode Fibre

Yangtze Optical Fibre and Cable Joint Stock Limited Company

YOFC OM2 (50/125 $\mu$ m) Bending Insensitive Multimode Fibre complies with or exceeds ISO/IEC 11801-1 OM2 specification, IEC 60793-2-10 A1-OM2 specification, and TIA-492AAAF A1-OM2 specification.

Features	Benefits and Applications
<ul style="list-style-type: none"> <li>• Superior geometry uniformity</li> <li>• Low attenuation</li> <li>• High bandwidth at wavelengths of 850nm and 1300nm</li> <li>• Manufactured by PCVD process</li> <li>• Extremely refined refractive index profile</li> </ul>	<ul style="list-style-type: none"> <li>• Local area networks (LAN)</li> <li>• Video, voice and data services</li> <li>• Gigabit Ethernet using laser or LED light sources</li> </ul>
<ul style="list-style-type: none"> <li>• Very low macro-bending sensitivity</li> </ul>	<ul style="list-style-type: none"> <li>• Supports the use and installation of optical cables with a small bending radius</li> </ul>
<ul style="list-style-type: none"> <li>• Coated with YOFC's proprietary dual layer UV curable acrylate</li> </ul>	<ul style="list-style-type: none"> <li>• High resistance to micro-bending</li> <li>• Optimized performance in tight-buffer cable applications</li> <li>• Stable performance over a wide range of environmental conditions</li> </ul>

Characteristics	Conditions	Specified values	Units
<b>Geometry Characteristics</b>			
Core Diameter	--	50±2.5	[µm]
Core Non-Circularity	--	≤5.0	[%]
Cladding Diameter	--	125.0±1.0	[µm]
Cladding Non-Circularity	--	≤1.0	[%]
Coating Diameter	--	245±7	[µm]
Coating/Cladding Concentricity Error	--	≤10.0	[µm]
Coating Non-Circularity	--	≤6.0	[%]
Core/Cladding Concentricity Error	--	≤1.5	[µm]
Delivery Length	--	up to 17.6	[km/reel]
<b>Optical Characteristics</b>			
Attenuation	850nm	≤2.3	[dB/km]
	1300nm	≤0.6	[dB/km]
Overfilled Modal Bandwidth	850nm	≥500	[MHz·km]
	1300nm	≥500	[MHz·km]
Numerical Aperture	--	0.200±0.015	--
Group Refractive Index	850nm	1.482	--
	1300nm	1.477	--
Zero Dispersion Wavelength, $\lambda_0$	--	1295-1340	[nm]
Zero Dispersion Slope, $S_0$	1295nm≤ $\lambda_0$ ≤1310nm	≤0.105	[ps/(nm <sup>2</sup> ·km)]
	1310nm≤ $\lambda_0$ ≤1340nm	≤0.000375 (1590- $\lambda_0$ )	[ps/(nm <sup>2</sup> ·km)]
Macrobending Loss	--	--	--
2 Turns @ 15 mm Radius	850nm	≤0.1	[dB]
	1300nm	≤0.3	[dB]
2 Turns @ 7.5 mm Radius	850nm	≤0.2	[dB]
	1300nm	≤0.5	[dB]
<b>Backscatter Characteristics</b>			
<b>1300nm</b>			
Step (Mean of Bidirectional Measurement)	--	≤0.10	[dB]
Irregularities Over Fibre Length and Point Discontinuity	--	≤0.10	[dB]
Attenuation Uniformity	--	≤0.08	[dB/km]
<b>Environmental Characteristics</b>			
<b>850nm &amp; 1300nm</b>			
Temperature Cycling	-60°C to 85°C	≤0.10	[dB/km]
Temperature-Humidity Cycling	-10°C to 85°C, 4% to 98% RH	≤0.10	[dB/km]
Water Immersion	23°C, 30 days	≤0.10	[dB/km]
Dry Heat	85°C, 30 days	≤0.10	[dB/km]
Damp Heat	85°C, 85% RH, 30 days	≤0.10	[dB/km]
<b>Mechanical Specification</b>			
Proof Test	--	≥9.0	[N]
	--	≥1.0	[%]
	--	≥100	[kpsi]
Coating Strip Force	typical average force	1.5	[N]
	peak force	≥1.3, ≤8.9	[N]
Dynamic Stress Corrosion Susceptibility Parameter ( $n_d$ , typical)	--	20	--